

LUSTER SHIELD 350

PRODUCT CODE: 004-LS350

350 VOC, HIGH GLOSS, UV RESISTANT 25% ACRYLIC COPOLYMER CONCRETE SEALER

PRODUCT DESCRIPTION

Luster Shield 350 is a high gloss, 350 VOC, UV Resistant acrylic copolymer concrete cure & seal intended for all types of concrete. Luster Shield 350 offers improved resistance to rain, the sun, freezing temperatures, stains, and other pollutants that can be hazardous to concrete. With substrate wetting agents and anti-foaming additives included in this formulation, Luster Shield 350 provides superior adhesion to properly prepared concrete. Applying Luster Shield 350 to exposed aggregate will also help to eliminate loose pebbles and premature wear. Luster Shield 350 can be considered an ultimate multi-use concrete sealer.

BENEFITS/FEATURES

- ◆ Can be used as a means of dustproofing most concrete surfaces.
- ◆ Provides superior resistance to the Sun's harsh ultraviolet rays for additional life of the coating.
 - ◆ Formulated at a medium viscosity allows for easy application through sprayers.
- ◆ Multi purpose protective sealer. Cure & Seal and long term Non-Yellowing protective sealer.

RECOMMENDED APPLICATIONS

Luster Shield 350 is recommended for use on Stamped Concrete, Stenciled Concrete, Acid Stained Concrete, Overlaid Concrete, Exposed Aggregate Concrete, Broom Finish Concrete, and Trowel Finish Concrete. Other uses may be acceptable.

TECHNICAL INFORMATION

Solids.....	25%	Wet Appearance.....	Clear to lightly cloudy
Drying Time.....	1 - 2 hours	Dry Appearance.....	Clear and Medium Gloss
Re-Coat Time.....	4 - 24 hours	VOC Content.....	<350 g/l
Foot Traffic.....	4 - 6 hours	Blush Resistance.....	Good
Wheel Traffic.....	24 - 48 hours	Solvent Resistance.....	Minimal
Application Temp.....	40°F - 85°F	Concrete Adhesion.....	Excellent

***Please note that low air and/or concrete temperatures and/or relative humidity may extend drying times. Follow recommended coverage rates for best results.

SPECIFICATIONS/COMPLIANCES

ASTM C 309, Type 1, Class A & B *ASTM C 1315, Type 1, Class A AASHTO Specification M-148, Type 1, Class A & B DRIED COATING IS USDA ACCEPTED
OTC & LADCO VOC COMPLIANT

APPROXIMATE COVERAGE RATES

<u>Application Surface</u>	<u>First Coat</u>	<u>Optional Second Coat</u>
New (unsealed) concrete	250-350 ft ²	350-400 ft ²
Old (sealed) concrete	350-400 ft ²	350-400 ft ²

*Coverage rates vary depending upon surface porosity and texture, and application method. Excessive build up should be avoided.

SHELF LIFE

Luster Shield 350 has a shelf life of up to two years in it's original, sealed, unopened container.

PACKAGING

Luster Shield 350 is packaged in 1 gallon cans, 5 gallon pails, and 55 gallon drums.



SURFACE KOATINGS, INC.

134 Davis St. Portland, TN 37148
Phone: (615) 323-9461 Fax: (615) 323-9816
Visit us online at: www.SurfKcoat.com

LOW VOC SEALERS

LUSTER SHIELD 350

INSTRUCTIONS FOR USE

SURFACE PREPARATION: Concrete surface must be clean and free of all contaminants and water. Do not apply if rain is forecast within 24 hours. If moisture is present or if the surface is not clean and free of all contaminants, the sealer may have white spots and have premature delamination and failure.

Substrate temperature must be no less than 40 degrees F and not exceed 80 degrees F. If applied outside these limits the sealer may not achieve adequate film formation and may have excessive air entrapment, bubbles, blushing or hazing.

MIXING: Stir well before using. Material may separate during long term storage.

APPLICATION: Apply using a 3/8" – 1/2" nap roller cover using long even uniform strokes at approximately 250-400 square feet per gallon depending on porosity and texture of substrate. A Chapin style solvent resistant sprayer may be used as well. Do not allow to Puddle! Thick or puddle areas may prevent the solvent from evaporating and may be susceptible to moisture intrusion which may cause milky white spots. Applying too thin may cause sealer to prematurely delaminate, flake or wear away. Allow sealer to dry for 24 hours for light traffic and at least 48 hours for heavy traffic. If applying two coats, wait approximately 4 – 6 hours between coats.

FRESHLY PLACED CONCRETE: Horizontal surfaces must be finished and show no "sheen" from bleed water.

PLEASE NOTE: It is always recommended to test the product in a small, inconspicuous area (on the same concrete substrate) for desired results prior to application. Coverage rates may vary for all coatings and substrates depending on porosity, density, texture etc. If applying by spray method, extended coverage rates may be achieved, but be aware that less material will be applied and inadequate film formation or performance expectations may be limited. **DO NOT USE ON BRICK.**

CLEAN-UP

Use Xylene. Dispose of containers in accordance with local and federal regulations.

PRODUCT REMOVAL

Dried, cured sealer may be removed with a commercial paint stripper, such as *Citrus Strip 100* or by using a diamond grinding method, sandblasting method or similar mechanical action.

PRECAUTIONS AND LIMITATIONS

- ▶ **Luster Shield 350** will not freeze during storage, however, allow temperature to rise to 50 degrees F prior to application.
- ▶ All HVAC ventilation ducts should be somehow blocked prior to application so solvents fumes are not distributed.
- ▶ Keep away from open flames. **Luster Shield 350** is flammable and is very susceptible to ignition.
- ▶ It is not recommended to apply **Luster Shield 350** over carpet, tile, and other types of floor adhesives.
- ▶ Coverage rates depend upon many conditions including application method, surface porosity, applicator, ect.
- ▶ **Luster Shield 350** was designed for decorative concrete and to be applied in two thin coats, not one thick coat.
- ▶ Please be aware that this product when cured may be slippery when wet.
- ▶ **Luster Shield 350** is not resistant to brake fluid, gasoline, and many similar products.
- ▶ It is not recommended to thin **Luster Shield 350**. Improper thinning may cause sealer to delaminate in a short time frame.
- ▶ **Luster Shield 350** may darken the surface of many new and existing concrete slabs. Test prior to use.

SPECIAL NOTES

Please consult Material Safety Data Sheet (MSDS) and read Warranty information prior to use. This information can be requested by contacting customer service at 615-323-9461.

SURFKOAT™

SURFACE KOATINGS, INC.

134 Davis St. Portland, TN 37148
Phone: (615) 323-9461 Fax: (615) 323-9816
Visit us online at: www.SurfKcoat.com